

SIRION[®] EHW 2834

PRODUCT DATA SHEET
(provisional)

Description

Liquid hardener for both liquid and waterborne epoxy resins, based on amine adduct in water solution.

Applications

In combination with waterborne epoxy resins (for example: Eposir WD 711/A), Sirion EHW 2834 can be used to formulate varnishes, primers, enamels and top coat with higher chemical resistance. The main fields of application are metal coating (anticorrosion) and civil engineering.

Sales specification

Property	Value	Unit	Method
Appearance	Amber Transparent Liquid		SIR 10010
Gardner Color	12 max	Sc. Gardner	ASTM D 1544
Brookfield viscosity @ 25°C	10000 – 30000	mPa.s	ASTM D 2393

Typical Properties

Property	Typical value	U.M
Solids content	50	%
Amine Number	310	mg.KOH/gr
AHEW	180	g/eq
Suggested mix ratio with epoxy resin (EEW 190)	90 - 100	phr
Suggested mix ratio with epoxy resin WD 711/A	17	phr
Pot life on 200 g mix @25°C with epoxy resin (EEW 190) phr	60	min

Delivery packaging

Sirion EHW 2834 is supplied in 200 kg drums, 1000 kg IBC or bulk.

Storage Life

The material is stable for 12 month, when stored into the original sealed package, away from sunlight exposition and excessive heat

The suggested range of temperature for the storage is 5 - 35° . Below 5°C the material could be hazy and could be observed an increasing of viscosity; these aspects would be back on increasing of temperature. The material could be yellowish if exposed for prolonged periods over 35°C

Safety Information

Sirion EHW 2834 is not inflammable and no toxic effect has been reported. For further handling information please refers to the MSDS.

SIRION[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.