

SIRALES[®] PE 7860

PRODUCT
DATA SHEET
RS/320/031501/1

Description

Carboxylated polyester resin for outdoor powder coatings.

Experimental resin. The specifications could be refined without any notice. In case of any question, please contact our sales department.

Applications

Sirales PE 7860, in combination with HAA (ratio 95:5), makes achievable a powder coating durable for industrial and architectural purposes. Its low reactivity and low melt viscosity assures very good flow and surface appearance of powder coatings. Outgassing limit of paints based on it is enhanced of 20-30 microns than that of standard resins.

Curing cycles (real time)	10 ... 15 min. at 200°C
	15 ... 20 min. at 180°C

Sales specification

Property	Value	Unit	Method
Acid number	30 ... 38	mg KOH/gr	SIR 10328
Viscosity at 200°C (ICI cone plate)	1500 - 3500	mPa.s	SIR 10391
Colour ⁽¹⁾	2 max.	Sc. Gardner	ASTM D 1544

(1) Determined on 50% m/m solution on dimethylformamide.

Typical Properties

Property	Value	Unit	Method
Glass transition temperature ⁽²⁾	55	°C	ASTM D 3418

(2) Determined on DSC (Perkin Elmer mod Diamond) : 20°C/minute.

Supply Form

Product is available as irregular flakes packed in 25 kg polyethylene bags.

Storage stability

The product should be stored in the original bags kept tightly closed, away from sunshine and heat sources. Under these conditions and at a normal temperature (20°C) the resin should have a stability of one year.

Safety

The product is not flammable and no toxic effect has been determined.
Further informations are provided in the relevant safety data sheet.

SIRALES[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.