

SIRESTER[®] EC 0768/D

PRODUCT DATA SHEET
RP/0768D/012016

Description

Ortophtalic-neopentylc unsaturated polyester resin, diluted in styrene, with quick reactivity and medium-low viscosity.

Applications

SIRESTER EC 0768/D is particularly indicated in the production of filled systems and polymer concrete articles, with high percentage of mineral filler. The resin contains an additive that migrates on the surface in order to reduce styrene emission, and an internal demoulding agent.

Sales specification

Property	Value	Unit	Method
Acid number	< 18	mg KOH/gr	SIR 10231
Viscosity at 25 °C	380 - 420	mPa s	SIR 10017

Typical Properties

Property	Value	Unit	Method
Appearance	Clear liquid		SIR 10010
Styrene content	35	%	SIR 10352
Gel time at 20 °C ⁽¹⁾	5	minute	SIR 10420
Apha colour	< 100		SIR 10007
Stability at 65 °C	6	day	SIR 10242

(1) Formulation: 100 g resin + 0,20 ml Co(oct) 6% + 2.0 ml MEKP 50%.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

SIRESTER[®] EC 0768/D

PRODUCT DATA SHEET
RP/0768D/012016

Mechanical properties of pure cured resin

Property	Value	Unit	Method
Barcol hardness	50		EN 59
Flexural strength	130	MPa	EN 63
E-Module, flexion	3800	MPa	EN 63
Tensile strength	70	MPa	EN 61
E-Module, tension	3600	MPa	EN 61
Elongation at break	3,0	%	EN 61
HDT	70	°C	EN ISO 75 A

Supply Form

Product is available in a 225 Kg lined drum, 1000 Kg container or in bulk.

Storage stability

The product is stable for 6 months if stored in a stainless steel tank or lined drums (avoid glass fibre based containers or tin plated drums), at 20 °C temperature, in a dark/ventilated place. Keep away from iron and copper salts, organic and inorganic peroxides.

Safety

The product is flammable and harmful.

Further information is provided in the relevant safety data sheet.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.