

SIRESTER[®] FS 0800

PRODUCT DATA SHEET

RP/0800/122011

Description

Orthophthalic, unsaturated polyester resin, diluted in styrene, with high reactivity and medium viscosity.

Applications

SIRESTER FS 0800 is particularly suitable for applications where high HDT and high elongation at break values are requested. The resin conforms to the requirements of DIN 1140.

Sales specification

Property	Value	Unit	Method
Acid number	≤ 30	mg KOH/g	SIR 10231
Viscosity at 25 °C	300 – 400	mPa s	SIR 10015

Typical Properties

Property	Value	Unit	Method
Appearance	Clear liquid		SIR 10010
Styrene content	38	%	SIR 10352
Gel time at 25 °C ⁽¹⁾	18	minutes	SIR 10234
SPI	5	minutes	SIR 10232
peak temperature	220	°C	
time to peak	8	minutes	
Stability at 65 °C	6	days	SIR 10242

(1) Formulation: 100 g resin + 0,2 ml Co (oct.) 6% + 1,5 ml MEKP 50%

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

Mechanical properties of pure cured resin

Property	Value	Unit	Method
Barcol hardness	55		EN 59
Flexural strength	120	MPa	EN 63
E-Module, flexion	4100	MPa	EN 63
Tensile strength	70	MPa	EN 61
E-Module, tension	3800	MPa	EN 61
Elongation at break	3,5	%	EN 61
HDT	105	°C	EN ISO 75 A

Mechanical properties of glass fiber reinforced resin (glass/resin 30/70)

Property	Value	Unit	Method
Flexural strength	220	MPa	EN 63
E-Module, flexion	9500	MPa	EN 63
Tensile strength	100	MPa	EN 61
E-Module, tension	9000	MPa	EN 61

Supply Form

Product is available in a 225 Kg lined drum, 1000 Kg container or in bulk.

Storage stability

The product is stable for 6 months if stored in a stainless steel tank or lined drums (avoid glass fibre based containers or tin plated drums), at 20 °C temperature, in a dark/ventilated place. Keep away from iron and copper salts, organic and inorganic peroxides.

Safety

The product is flammable and harmful.

Further information is provided in the relevant safety data sheet.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.