

SIRESTER[®] FS 0995/C

PRODUCT DATA SHEET

RP/0995C/062013

Description

Unsaturated orthophthalic polyester resin, diluted in styrene, with low reactivity and medium viscosity.

Applications

SIRESTER FS 0995/C is a general purpose material, particularly suitable for filament winding processes.

Sales specification

Property	Value	Unit	Method
Acid number	< 30	mg KOH/gr	SIR 10231
Viscosity at 25 °C	470 - 570	mPa s	SIR 10017

Typical Properties

Property	Value	Unit	Method
Appearance	Clear liquid		SIR 10010
Styrene content	36	%	SIR 10352
Stability at 65 °C	6	day	SIR 10242
Gel time at 25 °C ⁽¹⁾	60	minute	SIR 10234

(1) Formulation: 100 g resin + 0,25 ml Co (Oct) 6% + 1,5 ml MEKP 50%

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

Mechanical properties of pure cured resin

Property	Value	Unit	Method
Barcol hardness	45		EN 59
Flexural strength	100	MPa	EN 63
E-Module, flexion	4800	MPa	EN 63
Tensile strength	65	MPa	EN 61
E-Module, tension	4300	MPa	EN 61
Elongation at break	2,0	%	EN 61
HDT	75	°C	EN ISO 75 A

Mechanical properties reinforced resin (glass/resin 30/70)

Property	Value	Unit	Method
Flexural strength	220	MPa	EN 63
E-Module, flexion	9000	MPa	EN 63
Tensile strength	100	MPa	EN 61
E-Module, tension	9000	MPa	EN 61

Supply Form

Product is available in a 225 kg lined drum, 1000 kg container and bulk.

Storage stability

The product is stable for 6 months if stored in lined steel drums or in stainless steel tankers at 20 °C, away from sources of light and free of iron or copper salts, organic and inorganic peroxides.

Safety

The product is flammable and harmful.

Further information is provided in the relevant safety data sheet.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.