

Description

Unsaturated isophthalic polyester resin, diluted in styrene, with medium-low reactivity and medium viscosity, thixotropic and pre-accelerated.

Applications

SIRESTER ISN 0841/ATF/E is a general purpose material, particularly suitable for nautical applications and industrial parts, when good mechanical strengths and chemical resistance are required; its particular formulation grants high wettability and allows perfect workability also in vertical laminates.

Sales specification

Property	Value	Unit	Method
Acid number	≤ 18	mg KOH/g	SIR 10231

Typical Properties

Property	Value	Unit	Method
Appearance	Turbid blue liquid		SIR 10010
Styrene content	42	%	SIR 10352
Gel time at 20 °C ⁽¹⁾	40	minute	SIR 10284
Thixotropic index	> 3,0		
- 2 rpm	> 2400	mPa s	SIR 10215
- 20 rpm	< 800	mPa s	
Stability at 65 °C	6	day	SIR 10242

(1) Formulation: 100 g resin + 2,00 ml MEKP-50

During long storage a slight increase of the gel time can occur: we suggest to adjust the amount of catalyst in order to obtain correct values.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

Mechanical properties of pure cured resin

Property	Value	Unit	Method
Barcol hardness	40		EN 59
Flexural strength	130	MPa	EN 63
E-Module, flexion	3900	MPa	EN 63
Tensile strength	75	MPa	EN 61
E-Module, tension	3500	MPa	EN 61
Elongation at break	2,5	%	EN 61
HDT	85	°C	EN ISO 75 A

Mechanical properties of glass fiber reinforced resin (glass/resin: 30/70)

Property	Value	Unit	Method
Flexural strength	220	MPa	EN 63
E-Module, flexion	9200	MPa	EN 63
Tensile strength	110	MPa	EN 61
E-Module, tension	9200	MPa	EN 61

Supply Form

Product is available in a 225 Kg lined drum, 1000 Kg container or in bulk.

Storage stability

The product is stable for 3 months if stored in lined steel drums or in stainless steel tankers at 20 °C, away from sources of light and free of iron or copper salts, organic and inorganic peroxides. A long period of storage can cause slight segregation of the solid part of the product: stirring the material before using is strictly suggested.

Safety

The product is flammable and harmful.

Further information is provided in the relevant safety data sheet.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.