

SIRESTER[®] EC 0947/AMTV

PRODUCT DATA SHEET
RP/EC0947AMTV/052021

Description

Unsaturated orthophthalic polyester resin, diluted in styrene, with medium reactivity and medium viscosity, thixotropic and preaccelerated with catalyst indicator.

Applications

SIRESTER EC 0947/AMTV is a general purpose resin, with good mechanical strengths and excellent wetting properties, suitable in particular for HLU/SU applications; it contains an additive which appears on the surface reducing drastically the styrene emission: it is suggested to abrade the hardened surface before applying other layers.

Sales specification

Property	Value	Unit	Method
Acid number	≤ 30	mg KOH/gr	SIR 10231

Typical Properties

Property	Value	Unit	Method
Appearance	Blue hazy		SIR 10010
Styrene content	40	%	SIR 10257
Thixotropic index at 25 °C	> 3,0		
- 2 rpm	> 2100	mPa s	SIR 10215
- 20 rpm	< 700	mPa s	
Gel time at 25 °C ⁽¹⁾	26	minute	SIR 10267
Hardening time	50	minute	SIR 10267
Exothermic peak	140	°C	SIR 10267
Styrene emission	< 50	g/m ²	SIR 10295
Stability at 65 °C	6	day	SIR 10242

(1) Formulation: 100 gr resin + 1,50 ml MEKP-50.

During long storage a slight increase of the gel time can occur: we suggest to adjust the amount of catalyst in order to obtain correct values.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

Mechanical properties of pure cured resin (*)

Property	Value	Unit	Method
Barcol hardness	45		EN 59
Flexural strength	100	MPa	ISO 178
E-Module, flexion	4100	MPa	ISO 178
Tensile strength	60	MPa	EN ISO 527
E-Module, tension	3800	MPa	EN ISO 527
Elongation at break	2,0	%	EN ISO 527
HDT	70	°C	EN ISO 75 A

(*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

Mechanical properties of the reinforced resin (glass/resin 30/70) (*)

Property	Value	Unit	Method
Flexural strength	210	MPa	ISO 14125
E-Module, flexion	8600	MPa	ISO 14125
Tensile strength	100	MPa	EN ISO 527
E-Module, tension	8800	MPa	EN ISO 527

(*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

Supply Form

Product is available in a 225 kg lined drum, 1000 kg container or in bulk.

Storage guidelines

The product is stable for 6 months if stored in the original unopened packaging, below 30 °C and away from direct sunlight and heat sources. Keep away from iron and copper salts, organic and inorganic peroxides. Thixotropy properties are guaranteed for 3 months: a long period of storage can cause slight segregation of the solid part of the product. Stir the resin before use.

Safety

The product is flammable and harmful. Further information is provided in the relevant safety data sheet.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.