

# SIRION<sup>®</sup> FG 3706

## PRODUCT DATA SHEET

FG/3706/122011

### Description

Solution of a polyacrilate.

### Application

SIRION<sup>®</sup> FG 3706 is an additive able to improve flow and leveling in unsaturated polyester resins, polyurethane resins and solvent free epoxy resins.

### Sales specification

Property	Value	Unit	Method
Appearance	Clear or hazy liquid		SIR 10010
Gardner colour	1 max		SIR 10007

### Typical properties

Property	Value	Unit	Method
Refractive index at 25 °C	1.482		SIR 10018
Solid content	50	%	SIR 10257

### Recommended dosage and incorporation

It is possible to add SIRION<sup>®</sup> FG 3706 before or after any other component. The correct amount is between 0.5 and 1.5%, based on resin quantity.

### Supply form

The product is available in a 180 Kg lined drum and in 20 Kg containers.

### Storage stability

The product is stable for more than 6 months if it is stored in closed original containers.

### Safety

The product is flammable and harmful. Further information is provided in the relevant safety data sheet.

SIRESTER<sup>®</sup>: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.