

SIRESTER[®] FS 0940/RD

**PRODUCT DATA
SHEET**
RP/0940RD/052021

Description

Unsaturated orthophthalic polyester resin, diluted in styrene, with medium-fast reactivity and low viscosity. The resin contains a demoulding agent.

Applications

SIRESTER FS 0940/RD is suitable in particular for closed moulding applications as RTM manufacturing technology: it provides excellent wetting properties, fast curing cycle and high mechanical strengths.

Sales specification

Property	Value	Unit	Method
Acid number	≤ 27	mg KOH/gr	SIR 10231
Viscosity at 25 °C	150 - 250	mPa s	SIR 10015

Typical Properties

Property	Value	Unit	Method
Appearance	Clear liquid		SIR 10010
Styrene content	38	%	SIR 10257
Gel time at 25 °C ⁽¹⁾	10	minute	SIR 10234
Gel to peak time	10	minute	SIR 10234
Exothermic peak	190	°C	SIR 10234
Stability at 65 °C	6	day	SIR 10242

(1) Formulation: 100 gr resin + 0,20 ml Co (Octoate) 6% + 1,50 ml MEKP-50.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

SIRESTER[®] FS 0940/RD

**PRODUCT DATA
SHEET**
RP/0940RD/052021

Mechanical properties of pure cured resin (*)

Property	Value	Unit	Method
Barcol Hardness	55		EN 59
Flexural strength	130	MPa	ISO 178
E-Module, flexion	3800	MPa	ISO 178
Tensile strength	80	MPa	EN ISO 527
E-Module, tension	3600	MPa	EN ISO 527
Elongation at break	3,0	%	EN ISO 527
HDT	75	°C	EN ISO 75 A

(*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

Mechanical properties of the reinforced resin (glass/resin 30/70) (*)

Property	Value	Unit	Method
Flexural strength	220	MPa	ISO 14125
E-Module, flexion	9000	MPa	ISO 14125
Tensile strength	120	MPa	EN ISO 527
E-Module, tension	9600	MPa	EN ISO 527

(*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

Supply Form

Product is available in a 225 kg lined drum, 1000 kg container or in bulk.

Storage guidelines

The product is stable for 6 months if stored in the original unopened packaging, below 30 °C and away from direct sunlight and heat sources. Keep away from iron and copper salts, organic and inorganic peroxides.

Safety

The product is flammable and harmful. Further information is provided in the relevant safety data sheet.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.