

SIRESTER® IS 0785

**PRODUCT DATA
SHEET**
RP/0785/052021

Description

Unsaturated polyester resin based on neopentylglycol, diluted in styrene, with medium reactivity and medium-high viscosity.

Applications

SIRESTER IS 0785 is particularly suitable for piping and tank production by filament winding technology: it provides good wetting of the glass fibre, excellent mechanical properties and high chemical resistance. Drinkable water contact certification n° 067/12 by Politecnico di Milano.

Sales specification

Property	Value	Unit	Method
Acid number	≤ 15	mg KOH/gr	SIR 10231
Viscosity at 25 °C	700 – 900	mPa s	SIR 10017

Typical Properties

Property	Value	Unit	Method
Appearance	Clear to light hazy		SIR 10010
Styrene content	37	%	SIR 10257
Gel time at 25 °C ⁽¹⁾	28	minute	SIR 10234
Gel to peak time	13	minute	SIR 10234
Exothermic peak	180	°C	SIR 10234
Stability at 65 °C	6	day	SIR 10242

(1) Formulation: 100 gr resin + 0,20 ml Co (Oct) 6% + 1,50 ml MEKP-50.

SIRESTER®: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

SIRESTER[®] IS 0785

**PRODUCT DATA
SHEET**
RP/0785/052021

Mechanical properties of pure cured resin (*)

Property	Value	Unit	Method
Barcol hardness	50		EN 59
Flexural strength	120	MPa	ISO 178
E-Module, flexion	4100	MPa	ISO 178
Tensile strength	75	MPa	EN ISO 527
E-Module, tension	3700	MPa	EN ISO 527
Elongation at break	3,0	%	EN ISO 527
HDT	105	°C	EN ISO 75 A

(*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

Mechanical properties of glass fibre reinforced resin (glass/resin 30/70) (*)

Property	Value	Unit	Method
Flexural strength	210	MPa	ISO 14125
E-Module, flexion	8500	MPa	ISO 14125
Tensile strength	110	MPa	EN ISO 527
E-Module, tension	8800	MPa	EN ISO 527

(*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

Supply Form

Product is available in a 225 kg lined drum, 1000 kg container or in bulk.

Storage guidelines

The product is stable for 6 months if stored in the original unopened packaging, below 30 °C and away from direct sunlight and heat sources. Keep away from iron and copper salts, organic and inorganic peroxides.

Safety

The product is flammable and harmful. Further information is provided in the relevant safety data sheet.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.