

SIRESTER® IS 4240/P

**PRODUCT DATA
SHEET**
RP/4240P/052021

Description

Isophthalic unsaturated polyester resin, diluted in styrene, with medium reactivity and medium-high viscosity.

Applications

SIRESTER IS 4240/P is suitable for the production of composite materials, where good chemical resistance is required, in particular for pultrusion; it provides good wetting properties and superior mechanical strengths; properly fabricated and postcured parts conform type 1140 according to DIN 16946/2, and may be used for food contact applications according to UE n° 10/2011.

Sales specification

Property	Value	Unit	Method
Acid number	< 20	mg KOH/gr	SIR 10231
Viscosity at 25 °C	700 - 900	mPa s	SIR 10017

Typical Properties

Property	Value	Unit	Method
Appearance	Clear yellowish		SIR 10010
Styrene content	35	%	SIR 10257
Hazen colour	< 200	Sc. Pt/Co	SIR 10007
Gel time at 25 °C ⁽¹⁾	6	minutes	
Curing time	12	minutes	SIR 10234
Exothermic peak	215	°C	
Stability at 65 °C	6	days	SIR 10242

(1) Formulation: 100 gr resin + 0,20 ml Co (Oct) 6% + 1,50 ml MEKP-50.

SIRESTER®: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

SIRESTER[®] IS 4240/P

**PRODUCT DATA
SHEET**
RP/4240P/052021

Mechanical properties of pure cured resin (*)

Property	Value	Unit	Method
Barcol hardness	50		EN 59
Flexural strength	140	MPa	ISO 178
E-Module, flexion	4300	MPa	ISO 178
Tensile strength	75	MPa	EN ISO 527
E-Module, tension	3900	MPa	EN ISO 527
Elongation at break	2,0	%	EN ISO 527
HDT	105	°C	EN ISO 75 A

(*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

Mechanical properties of glass fibre reinforced resin (glass/resin 30/70) (*)

Property	Value	Unit	Method
Flexural strength	230	MPa	ISO 14125
E-Module, flexion	9200	MPa	ISO 14125
Tensile strength	110	MPa	EN ISO 527
E-Module, tension	8800	MPa	EN ISO 527

(*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

Supply Form

Product is available in a 225 kg lined drum, 1000 kg container or in bulk.

Storage guidelines

The product is stable for 6 months if stored in the original unopened packaging, below 30 °C and away from direct sunlight and heat sources. Keep away from iron and copper salts, organic and inorganic peroxides.

Safety

The product is flammable and harmful. Further information is provided in the relevant safety data sheet.

SIRESTER[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.