

# SIRESTER<sup>®</sup> ISG 0839/MMA

**PRODUCT DATA  
SHEET**  
RP/0839MMA/052021

## Description

Isophthalic unsaturated polyester resin based on neopentylglycol, diluted in styrene and acrylic-modified, preaccelerated with medium reactivity and medium-high viscosity. The resin is UV stabilized.

## Applications

SIRESTER ISG 0839/MMA is particularly suitable for solid surface applications, as fully densified products like onyx, sanitary and marble imitations, where high chemical and weathering resistance are required.

## Sales specification

Property	Value	Unit	Method
Acid number	≤ 16	mg KOH/gr	SIR 10231
Viscosity at 25 °C	1050 – 1100	mPa s	SIR 10017

## Typical Properties

Property	Value	Unit	Method
Appearance	Clear to hazy		SIR 10010
Colour	Rose		SIR 10007
Monomer content	34	%	SIR 10257
Gel time at 25 °C <sup>(1)</sup>	26	minute	SIR 10267
Curing time	36	minute	SIR 10267
Exothermic peak	200	°C	SR 10267
Stability at 65 °C	6	day	SIR 10242

(1) Formulation: 100 gr resin + 1,50 ml MEKP-50.

During long storage a slight increase of the gel time can occur: we suggest to adjust the amount of catalyst in order to obtain correct values.

SIRESTER<sup>®</sup>: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

# SIRESTER<sup>®</sup> ISG 0839/MMA

**PRODUCT DATA  
SHEET**  
RP/0839MMA/052021

## Mechanical properties of pure cured resin (\*)

Property	Value	Unit	Method
Barcol hardness	48		EN 59
Flexural strength	130	MPa	ISO 178
E-Module, flexion	4000	MPa	ISO 178
Tensile strength	75	MPa	EN ISO 527
E-Module, tension	3600	MPa	EN ISO 527
Elongation at break	2,0	%	EN ISO 527
HDT	95	°C	EN ISO 75 A

(\*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

## Mechanical properties of the reinforced resin (glass/resin 30/70) (\*)

Property	Value	Unit	Method
Flexural strength	210	MPa	ISO 14125
E-Module, flexion	8400	MPa	ISO 14125
Tensile strength	110	MPa	EN ISO 527
E-Module, tension	8500	MPa	EN ISO 527

(\*) Typical properties, not suitable for specification; postcuring cycle: 24 hours 25 °C + 2 hours 100 °C

## Supply Form

Product is available in a 225 kg lined drum, 1000 kg container or in bulk.

## Storage guidelines

The product is stable for 6 months if stored in the original unopened packaging, below 30 °C and away from direct sunlight and heat sources. Keep away from iron and copper salts, organic and inorganic peroxides.

## Safety

The product is flammable and harmful. Further information is provided in the relevant safety data sheet.

SIRESTER<sup>®</sup>: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.