# SIRION® VP 2085

PRODUCT DATA SHEET

REC/2085/0314/1 Revised: August 2018

### **Description**

Solid unmodified phenolic hardener for epoxy resins. The product does not contain curing accelerator and flow agent.

## **Applications**

Sirion VP 2085 is suitable for formulation of decorative or protective epoxy based powder coatings. When formulated with epoxy resins, cured coatings with good flexibility and chemical resistances can be obtained. It is useful, in combination with other Sirion VP 208xx series products, for optimizing the reactivity of powder coating formulations which already contain a curing accelerator.

## **Sales specification**

Property	Value	Unit	Method
Melting range	60 - 70	$^{\circ}\mathrm{C}$	SIR 10000
Viscosity at 25°C (1)	H - M	Gardner Sc.	ASTM D 1545
Colour (1)	200 max.	Pt/Co Sc.	ASTM D 1209

<sup>(1)</sup> Determined on 40% m/m solution diethylenelycol-monobutylether.

#### **Typical Properties**

Property		Value	Unit	Method
Active hydrogen equiv.	weight	$250\pm30$	g/eq.	
Glass transition temperat	ture (2)	52	$^{\circ}\mathrm{C}$	ASTM D 3418
Viscosity at 150°C	(3)	700	mPa.s	SIR 10391

<sup>(2)</sup> Determined on DSC (Perkin Elmer series 7): 20°C/minute.

#### Storage stability

The product should be stored in the original bags kept tightly closed, away from sunshine and heat sources. Under these conditions and at a normal temperature (20°C) the resin should have a stability of one year.

#### Safety

The product is not labelled as flammable. Please consult safety data sheet for complete details.

Eposir ®: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.

<sup>(3)</sup> ICI Cone & Plate Viscosimeter