

SIRALES[®] PE 6220

PRODUCT
DATA SHEET
RS/093/070903/1

Description

Hydroxylated polyester resin with good weathering resistance.

Applications

Sirales PE 6220 is suitable for preparation of masterbatches with additives and pigments commonly used in thermosetting powder coating production.

Its particular composition guarantee optimum compatibility, fillers and pigments wettability and resistance to ageing.

Sales specification

Property	Value	Unit	Method
Acid number	5 max	mg KOH/gr	SIR 10328
Hydroxyl number	62 – 75	mgKOH/gr	SIR 10299
Viscosity ICI at 200°C	500 – 2500	mPa.s	SIR 10391

Typical Properties

Property	Value	Unit	Method
Glass transition temperature	50	°C	ASTM D 3418

Supply Form

Product is available as irregular flakes packed in 25 Kg polyethylene bags.

Storage stability

The product should be stored in the original bags kept tightly closed, away from sunshine and heat sources. Under these conditions and at a normal temperature (25°C max) the resin should have a stability of one year.

Safety

The product is not flammable and no toxic effect has been determined.
Further information are provided in the relevant safety data sheet.

SIRALES[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.