

SIRALES[®] PE 7400

PRODUCT
DATA SHEET
RS/134/091702/1

Description

Masterbatch to increase tribostatic properties of powder coatings. SIRALES[®] PE 7400 contains 5% of active substance dispersed in carboxylated polyester resin suitable for outdoor powder coatings.

Applications

SIRALES[®] PE 7400, employed in an amount from 2 to 4%, increases greatly the tribostatic chargeability of a powder coating. It can be employed in indoor and outdoor powder coatings without affects gel time and storage stability of the paints. The masterbatch is easy handling and ensures a very good dispersion of the tribo additive.

Sales specifications

Property	Value	Unit	Method
Acid number	30 - 38	mg KOH/gr	SIR 10328
Viscosity at 200°C (ICI cone plate)	2000 - 4000	mPa.s	SIR 10391
Colour ⁽¹⁾	3 max.	Sc. Gardner	ASTM D 1544

(1) Determined on 50% m/m solution on dimethylformamide.

Typical Properties

Property	Value	Unit	Method
Glass transition temperature (Tg)	60	°C	ASTM D 3418

Supply Form

Product is available as irregular flakes packed in 25 kg Polyethylene bags.

Storage stability

The product should be stored in the original bags kept tightly closed, away from sunshine and heat sources. Under these conditions and at a normal temperature (not more than 25°C) the resin should have a stability of one year.

Safety

The product is not flammable and no toxic effect has been determined.

Further information are provided in the safety data sheet.

SIRALES[®]: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.