

SIRALES[®] PE 8222.T

PRODUCT
DATA SHEET
RS/8222T/030201/1

Description

Carboxylated polyester resin suitable for HYBRID powder coatings.

Applications

Sirales[®] PE 8222.T is suggested in combination 60/40 and/or 50/50 p.b.w. with EPOSIR[®] 7168 PG, EPOSIR[®] 7175 PG or EPONAC[®] 825, to manufacture powder coatings with high reactivity, very good flow and gloss.

Powder coatings manufactured with SIRALES[®] PE 8222.T are suitable for tribo gun applications.

Curing cycles (real time) 10 min. at 180°C
 15 min. at 160°C

Sales specification

Property	Value	Unit	Method
Acid number	60 ... 72	mg KOH/gr	SIR 10328
Viscosity at 200°C (ICI cone plate)	1800 ... 3800	mPa.s	SIR 10391
Colour (1)	3 max.	Gardner unit	ASTM D 1544

(1) Determined on 50% m/m solution on dimethylformamide.

Typical Properties

Property	Value	Unit	Method
Glass transition temperature	55	°C	ASTM D 3418

Supply Form

Product is available as irregular flakes packed in 25 kg Polyethylene bags.

Storage stability

The product should be stored in the original bags kept tightly closed, away from sunshine and heat sources. Under these conditions and at a normal temperature (20°C) the resin should have a stability of one year.

Safety

The product is not flammable and no toxic effect has been determined.

Further informations are provided in the relevant safety data sheet.

SIRALES[®], EPOSIR[®] and EPONAC[®] are SIR INDUSTRIALE SpA registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.