

# SIRALES<sup>®</sup> PE 8470

PRODUCT  
DATA SHEET  
RS/8470/040801/1

## Description

Carboxylated polyester resin suitable for epoxy polyester powder coatings based on FDA approved raw materials - 21 CFR Ch. I (4– 1– 06 Edition) § 175.300 for contact with non alcoholic foods.

## Applications

Sirales<sup>®</sup> PE 8470 is suggested in combination 70/30 p.b.w. with EPOSIR<sup>®</sup> 7167 PG or 7175 PG and EPONAC<sup>®</sup> 615 or 700, to manufacture powder coatings with good flow and mechanical properties and yellowing resistance for overbaking. To regulate curing cycles it is necessary to employ appropriate catalysts or accelerators like Sirion<sup>®</sup> VP 1110

## Curing cycles (real time)

It depends from catalyst employed.

## Sales specification

Property	Value	Unit	Method
Acid number	32 ... 40	mg KOH/gr	SIR 10328
Viscosity at 200°C (ICI cone plate)	3500 ... 5500	m.Pa.s.	SIR 10391
Colour (1)	3 max.	Sc. Gardner	ASTM D 1544

(1) Determined on 50% m/m solution on dimethylformamide.

## Typical Properties

Property	Value	Unit	Method
Glass transition temperature	55	°C	ASTM D 3418

## Supply Form

Product is available as irregular flakes packed in 25 kg Polyethylene bags.

## Storage stability

The product should be stored in the original bags kept tightly closed, away from sunshine and heat sources. Under these conditions and at a normal temperature (20°C) the resin should have a stability of one year.

## Safety

The product is not flammable and no toxic effect has been determined.  
Further information are provided in the relevant safety data sheet.

SIRALES<sup>®</sup>, EPOSIR<sup>®</sup>, EPONAC<sup>®</sup> and SIRION<sup>®</sup>: SIR INDUSTRIALE registered trade mark.

N.B.: The data given in this brochure do not constitute characteristic properties of the single product.

To our best knowledge, the information contained in this brochure is accurate and corresponds to the truth.

However, any recommendations or suggestions are provided without any guarantee, since the conditions in which the products are used are not under our control. Furthermore, nothing contained in this brochure shall be interpreted as a recommendation for using the product in violation of any patents relating to the material and their uses.