



SIR INDUSTRIALE SpA

PROSID® - β -hydroxyalkylamides

Hardener for Powder Coatings

PRODUCT	APPEARANCE	MELTING RANGE (°C)	HYDROXYL EW (g/eq)	DESCRIPTION
411	white flakes	116 – 126	84-88	Based on β -HAA it is suitable for production of outdoor powder coatings with a very high weathering resistance
H30A	white flakes	80 – 100	270-290	Masterbatch 30% β -HAA hardener with outdoor polyester resins
H50A	white flakes	80 – 100	170-180	Masterbatch 50% β -HAA hardener with outdoor polyester resins